AMPHIPHILIC POLYSACCHARIDE DERIVATIVES

BACKGROUND OF THE INVENTION

This invention relates to polysaccharide derivatives having increased hydrophobicity as compared to the unmodified polysaccharide. More particularly, the invention relates to

5   amphiphilic polysaccharide derivatives, such as amphiphilic heparin derivatives, wherein the bioactivity of the polysaccharide is preserved. Further, the invention relates to methods of making and using such amphiphilic polysaccharide derivatives.

Heparin is a polysaccharide composed of sulfated D-glucosamine and D-glucuronic acid residues. Due to its numerous ionizable sulfate groups, heparin possesses a strong

10   electronegative charge. It is also a relatively strong acid that readily forms water-soluble salts, e.g. heparin sodium. It is found in mast cells and can be extracted from many body organs, particularly those with abundant mast cells. The liver and lungs are especially rich in heparin. The circulating blood contains no heparin except after profound disruption of mast cells. Heparin has many physiological roles, such as blood anticoagulation, inhibition of smooth

15   muscle cell proliferation, and so forth. In particular, heparin is a potent anticoagulant agent that interacts strongly with antithrombin III to prevent the formation of fibrin clots. *In vivo*, however, applications of heparin are very limited. Because of its hydrophilicity and high negative charge, heparin is not absorbed efficiently from the GI tract, nasal or buccal mucosal layers, and the like. Therefore, the only routes of administration used clinically are intravenous and subcutaneous

20   injections. Moreover, since heparin is soluble in relatively few solvents, it is hard to use for coating surfaces of medical devices or in delivery systems.

1

2

To improve the properties of heparin, R.J. Linhardt et al., 83 J. Pharm. Sci. 1034-1039

(1994), coupled lauryl (C_{12}) and stearyl (C_{18}) groups to single heparin chains, resulting in a

derivatized heparin having increased hydrophobicity but with low anticoagulant activity. This

result demonstrated that coupling a small linear aliphatic chain to heparin was ineffective in

5   enhancing the hydrophobicity of heparin while preserving activity. Thus, known heparin

derivatives have been ineffective in preserving anticoagulation activity.

Rivera et al., Oral Delivery of Heparin in Combination with Sodium N-[8-(2-

Hydroxybenzolyl)amino]caprylate: Pharmacological Considerations, 14 Pharm. Res. 1830-1834

(1997), disclosed the possibility of oral delivery of heparin using heparin mixed with sodium N-

10   [8-(2-hydroxybenzolyl)amino]caprylate. Dryjski et al., Investigations on Plasma Activity of Low

Molecular Weight Heparin after Intravenous and Oral Administrations, 28 Br. J. Clin. Pharma.

188-192 (1989), described the possibility of oral absorption of low molecular weight heparin

using enhancers.

Two basic methods have been developed for the formulation of a heparin-releasing

15   system. One method involves binding heparin to a cationic polymer matrix by ionic bonds. The

release of heparin is controlled by an ion exchange mechanism. Another method involves

dispersed heparin, where heparin is first physically blended with a polymer, and then the release

of heparin is controlled by diffusion. The most simple and efficient method for preparing such a

heparin device is solvent casting. But a solvent casting method cannot be used for preparing the

20   heparin device since heparin is not dissolved in the organic solvent used for dissolving the

polymer. If heparin derivatives could be prepared with increased hydrophobicity while

maintaining bioactivity, then the heparin derivatives could be simply immobilized in a polymer

3

matrix by a solvent casting procedure.

In view of the foregoing, it will be appreciated that the development of a hydrophobic heparin derivative or amphiphilic heparin derivative having high bioactivity would be a significant advancement in the art. Such a hydrophobic heparin derivative could be used in a

5   controlled release system, for oral administration, or for surface modification of medical devices for improving biocompatibility. Such a heparin derivative would greatly extend the medical applications of heparin.

BRIEF SUMMARY OF THE INVENTION

It is an object of the present invention to synthesize amphiphilic heparin derivatives

10   having high heparin bioactivity.

It is also an object of the invention to provide a hydrophobic heparin derivative that is soluble in a solvent such as acetone/water, as well as water.

It is another object of the invention to provide heparin derivatives that can be used for a controlled release system to prevent coagulation at a surface.

15   It is still another object of the invention to provide heparin derivatives that can be absorbed from the GI tract, thereby facilitating oral delivery for preventing blood coagulation.

It is yet another object of the invention to provide heparin derivatives comprising heparin coupled with a bile acid, such as deoxycholic acid or glycocholic acid, or a hydrophobic agent, such as cholesterol, or an alkanoic acid.

20   These and other objects can be addressed by providing a composition of matter comprising a polysaccharide covalently bonded to a hydrophobic agent. Preferably, the

3

4

polysaccharide is a member selected from the group consisting of heparin, heparin sodium, sulfonated polysaccharides, cellulose, hydroxymethylcellulose, and hydroxypropylcellulose. An especially preferred polysaccharide is heparin. Preferably, such heparin has a molecular weight of about 200 to 100,000. In a preferred embodiment of the invention, the hydrophobic agent is a

5   member selected from the group consisting of bile acids, sterols, and alkanoic acids. Preferred bile acids include cholic acid, deoxycholic acid, chenodeoxycholic acid, lithocholic acid, ursocholic acid, ursodeoxycholic acid, isoursodeoxycholic acid, lagodeoxycholic acid, glycocholic acid, taurocholic acid, glycodeoxycholic acid, glycochenodeoxycholic acid, dehydrocholic acid, hyocholic acid, hyodeoxycholic acid, and mixtures thereof. Preferred sterols

10   include cholestanol, coprostanol, cholesterol, epicholesterol, ergosterol, ergocalciferol, and mixtures thereof. Preferred alkanoic acids comprise about 4 to 20 carbon atoms, such as butyric acid, valeric acid, caproic acid, caprylic acid, capric acid, lauric acid, myristic acid, palmitic acid, stearic acid, and mixtures thereof. Preferably the polysaccharide and the hydrophobic agent are present in a mole ratio of about 1:1 to 1:1000.

15   Another aspect of the invention comprises a pharmaceutical composition comprising a pharmaceutically effective amount of (a) a composition of matter comprising a polysaccharide covalently bonded to a hydrophobic agent, and (b) a pharmaceutically acceptable carrier. The pharmaceutically acceptable carrier can be an oral drug carrier, sustained release carrier, carrier for parenteral administration, and the like. Preferred sustained release carriers include polymeric

20   matrices such as are well known in the art, including members selected from the group consisting of poly(ethylene oxide)-poly(ε-caprolactone) copolymers, polyurethane polymers, silicone polymers, ethylene vinyl acetate polymers, hydrogels, collagen, gelatin, and mixtures thereof, and

4

5

the like.

Still another aspect of the invention comprises a method for inhibiting blood coagulation on medical devices that come in contact with blood comprising coating the medical device with a pharmaceutical composition comprising a polymeric matrix intimately admixed with a

5   composition of matter comprising heparin covalently bonded to a hydrophobic agent. Typically, the medical device is coated by using a film casting technique such as is well known in the art.

BRIEF DESCRIPTION OF THE SEVERAL VIEWS OF THE DRAWINGS

FIG. 1 shows bioactivity of hydrophobic heparin as determined by APTT (closed symbols) and chromogenic (open symbols) assay: ■ and □, deoxycholic acid (DOCA); ● and ○,

10   cholesterol; ▼ and ▽, palmitic acid; ▲ and △, lauric acid.

FIG. 2 shows clotting time as a function of time when low molecular weight heparin-DOCA is administered orally.

FIG. 3 shows clotting time as a function of time when high molecular weight heparin-DOCA is administered orally.

15   FIG. 4 shows cumulative heparin-DOCA conjugate release from a poly(ethylene oxide)-poly(ε-caprolactone) (PEO-PCL) polymeric matrix as a function of time; the weight % of heparin-DOCA in the polymeric matrix: (▽), 5% DOCA; (○), 10% DOCA; (△), 20% DOCA; (□), 30% DOCA.

DETAILED DESCRIPTION

20   Before the present amphiphilic polysaccharide composition and methods of making and

5

6

use thereof are disclosed and described, it is to be understood that this invention is not limited to the particular configurations, process steps, and materials disclosed herein as such configurations, process steps, and materials may vary somewhat. It is also to be understood that the terminology employed herein is used for the purpose of describing particular embodiments

5   only and is not intended to be limiting since the scope of the present invention will be limited only by the appended claims and equivalents thereof.

It must be noted that, as used in this specification and the appended claims, the singular forms "a," "an," and "the" include plural referents unless the context clearly dictates otherwise. Thus, for example, reference to "a bile acid" includes a mixture of two or more of such bile acids,

10   reference to "an alkanoic acid" includes reference to one or more of such alkanoic acids, and reference to "a sterol" includes reference to a mixture of two or more sterols.

In describing and claiming the present invention, the following terminology will be used in accordance with the definitions set out below.

As used herein, "bile acids" means natural and synthetic derivatives of the steroid,

15   cholanic acid, including, without limitation, cholic acid, deoxycholic acid, chenodeoxycholic acid, lithocholic acid, ursocholic acid, ursodeoxycholic acid, isoursodeoxycholic acid, lagodeoxycholic acid, glycocholic acid, taurocholic acid, glycodeoxycholic acid, glycochenodeoxycholic acid, dehydrocholic acid, hyocholic acid, hyodeoxycholic acid, and mixtures thereof, and the like.

20   As used herein, "sterols" means alcohols structurally related to the steroids including, without limitation, cholestanol, coprostanol, cholesterol, epicholesterol, ergosterol, ergocalciferol, and mixtures thereof, and the like.

7

As used herein, "alkanoic acids" means saturated fatty acids of about 4 to 20 carbon atoms. Illustrative alkanoic acids include, without limitation, butyric acid, valeric acid, caproic acid, caprylic acid, capric acid, lauric acid, myristic acid, palmitic acid, stearic acid, and mixtures thereof, and the like.

5   As used herein, "hydrophobic heparin derivative" and "amphiphilic heparin derivative" are used interchangeably. Heparin is a very hydrophilic material. Increasing the hydrophobicity of heparin by bonding a hydrophobic agent thereto results in what is termed herein an amphiphilic heparin derivative or hydrophobic heparin derivative. Either term is believed proper because the heparin derivative has increased hydrophobicity as compared to native heparin and

10   the heparin derivative has a hydrophilic portion and a hydrophobic portion and is, thus, amphiphilic.

          It is well known that heparin is used as an antithrombogenic agent to prevent blood coagulation. Heparin is highly hydrophilic because of a high density of negative charges such as are provided by sulfonic and carboxylic groups. Due to this hydrophilicity, heparin is usually

15   administered by intravenous or subcutaneous injection. Heparin derivatives with slightly hydrophobic properties or amphiphilic properties and with high bioactivity are described herein. Hydrophobic agents, such as bile acids, e.g. deoxycholic acid (DOCA); sterols, e.g. cholesterol; and alkanoic acids, e.g. lauric acid and palmitic acid, were coupled with heparin. Both deoxycholic acid and cholesterol are non-toxic since they are naturally occurring compounds

20   found in the body. The amine groups of heparin were coupled with carboxyl groups of the hydrophobic agents. The end carboxylic groups in DOCA, lauric acid, and palmitic acid were used directly for the coupling reaction, while the hydroxy group of cholesterol was activated by

7

reaction with chloroacetic acid before coupling. It was determined that conjugating such

hydrophobic moieties to the amine groups of heparin had little or no effect on heparin bioactivity.

The coupling between heparin and hydrophobic agents was confirmed by detecting the amide

bond by FT-IR and ^{13}C-NMR analysis.

5   The yield of the coupling reaction was about 70 to 80% and was not significantly changed

by changing the hydrophobic agents or feed molar ratios. In the case of the heparin-DOCA

conjugate, as the feed ratio was increased, the amount of DOCA in the conjugate was also

increased. The weight % of DOCA in heparin-DOCA was 24% when the feed molar ratio of

heparin to DOCA was 1:200. This molar ratio was very high compared to the ratio of amine

10   groups in heparin to DOCA. Therefore, this feed ratio is estimated as an excess amount of

DOCA.

          The hydrophobic heparin derivatives according to the present invention would have many

medical applications. For example, the hydrophobic heparin can be administered orally. The

oral administration of heparin can extend greatly the usage of heparin as an oral anti-coagulant

15   drug. The heparin derivative is formulated with a pharmaceutically acceptable carrier such as is

well known in the art. By way of further example, hydrophobic heparin derivatives can be used

as a coating material for medical devices such as catheters, cardiopulmonary bypass circuits, hear

lung oxygenators, kidney dialyzers, stent or balloon coating for preventing restenosis, and the

like. The hydrophobic heparin derivative is typically mixed with a carrier, and then coated on the

20   surface of the medical device by a film casting technique such as is well known in the art.

          After modification, heparin-hydrophobic agents were also found to have a tendency in

fast protein liquid chromatography (FPLC®) to exhibit hydrophobic interactions with

8

9

hydrophobic media, as shown by chromatography on Phenyl Sepharose® (eluting in ammonium sulfate buffer rather than phosphate buffer). These heparin derivatives showed enhanced binding affinity when compared to unmodified heparin. The increased interaction of modified heparin derivatives with Phenyl Sepharose® is attributable to its enhanced hydrophobicity, the result of

5   the hydrophobic functional groups present. These results suggest hydrophobic heparin can be obtained by conjugating a bile acid, sterol, or alkanoic acid to heparin. In solubility tests, polar solvents or organic solvents were suitable to dissolve the heparin-hydrophobic agent conjugates. For example, the heparin-deoxycholic acid conjugate showed good solubility in 65% acetone solution (35% water). Finally, it was determined that bioactivity of modified heparin derivatives

10   was not appreciably influenced by conjugation with hydrophobic agents. The role of a hydrophobic agent conjugated to heparin was studied with respect to two biological activities of heparin as determined by anticoagulation and factor Xa assays. Although hydrophobicity is associated with a somewhat reduced anticoagulant activity and antifactor Xa activity, the decrease of bioactivity was not considered serious. These results indicate that blocking the

15   amine groups of heparin had little effect on its bioactivity. The bioactivity of heparin in heparin-hydrophobic agent conjugates exhibited a progressive reduction, however, when the amount of hydrophobic agent in the conjugate exceeded 20 wt. %. At less than 20 wt. % of hydrophobic agent in the conjugates, the bioactivity of the conjugates was greater than 80% of the bioactivity of unmodified heparin. It is suggested that 80% of bioactivity in hydrophobic heparin is enough

20   to support bioactivity in medical applications.

9

Example 1

<u>Synthesis of Heparin-DOCA Conjugates</u>. Five ml of N-hydroxylsuccinimide (HOSu, 92

mg/5 ml) in dimethylformamide (DMF) was mixed with 5 ml of dicyclohexylcarbodiimide

(DCC) (165 mg/5 ml) in DMF, followed by adding 5 ml of DOCA (196 mg/5 ml) in DMF. The

5   mole ratio of DOCA, HOSu, and DCC was 1:1.6:1.6. The concentrations of HOSu and DCC

were slightly higher than that of DOCA to activate DOCA completely. The resulting solution

was reacted for 5 hours at room temperature under vacuum, and then the byproduct

dicyclohexylurea (DCU), which precipitated during the reaction, was removed. The unreacted

DCC was removed by adding a drop of distilled water and filtering. The remaining HOSu was

10   also removed by adding 15 ml of distilled water. The activated DOCA was precipitated and then

lyophilized. The activated DOCA was then dissolved in DMF and reacted with heparin for 4

hours at room temperature. The amounts of heparin used in such reactions ranged from 40 to

400 mg. After reaction, there were two types of products: a water soluble product and a water-

insoluble product. These products were separated by filtration through a 0.45 μm membrane

15   filter, and the water-insoluble product was dried in a vacumm oven. The water-soluble product

was dialyzed for 1 day against water using a membrane (MWCO 3,500), and then heparin-

DOCA was freeze dried.

The heparin derivatives prepared according to this procedure were characterized by FT-IR

and NMR according to methods well known in the art to prove the successful coupling between

20   heparin and the hydrophobic agent. The proof of the heparin derivatives is the amide bond

produced by the coupling of an amine group of heparin with a carboxyl group of the hydrophobic

agent. In the FT-IR spectrum, significant variation in the spectra was found in the range from

10

1740 to 1500 cm^{-1}. An intense band was observed at 1585 cm^{-1} and assigned to the amide

vibrations, which are correlated with the presence of amide bond between heparin and

hydrophobic agent. The peak of N-H groups in heparin part of heparin derivative appeared

around 3500 ad 1620 cm^{-1}, respectively. The ^{13}C-NMR spectrum of the heparin-DOCA

5   conjugate showed characteristic absorption peaks at δ 7.58(carbon at amine bond), 5.5(H-1 of

glucosamine 2,6-disulfate), δ 5,35(H-1 of glucosamine 2-sulfate), δ 5.2(H-1 of iduronic acid 2-

sulfate). ^{13}C-NMR spectra in a comparison of heparin-DOCA and heparin showed different

peaks at 178 ppm (carbon at amine bond). These results confirm the presence of an amide bond

in the heparin-DOCA conjugate, demonstrating the coupling of an amine group of heparin to a

10   carboxyl group of DOCA.

Example 2

Preparation of Heparin-Cholesterol Conjugates. The hydroxyl group of cholesterol was

activated by reaction with chloroacetic acid to result in a free carboxyl group. The modified

cholesterol was reacted with HOSu and DCC in 10 ml of DMF. The mole ratio of cholesterol,

15   HOSu, and DCC was 1:1.6:1.6 and reaction was for 5 hours at room temperature. To remove the

unreacted DCC and HOSu, water was added and the solution was filtered with a 0.45 μm

membrane. Next, the activated cholesterol was reacted with heparin solution for 4 hours. Two

products, a water-soluble product and a water-insoluble product, were obtained from the reaction.

These products were treated according to the procedure described above in Example 1.

Example 3

Synthesis of Heparin-Alkanoic Acid Conjugates. Lauric acid and palmitic acid were coupled to heparin according to the procedure of Example 1. The carboxyl group of the alkanoic acids were coupled with amine groups of heparin to form amide bonds. Coupling agents were

5   also HOSu and DCC.

For heparin-DOCA, heparin-cholesterol, and heparin-alkanoic acid, the production yield, molecular weight, and binding mole ratios between heparin and hydrophobic agents varied according to the mole ratio of reactants. The yield of heparin-DOCA conjugates was in the range from 71 to 77%. The molecular weight of heparin was determined as 12,386 daltons by light

10   scattering. The amount of hydrophobic agent in modified heparin derivatives was calculated by subtracting the heparin molecular weight from the measured molecular weight of each heparin derivative. As the feed mole ratio of deoxycholic acid to heparin was increased from 1:6 to 1:200, the amount of DOCA in heparin-DOCA conjugates was increased from 7 to 24%. For the heparin-cholesterol conjugates, the yield also was in the range from 73 to 78%. The amount of

15   cholesterol in such hydrophobic heparin conjugates, however, was slightly lower than the amount of DOCA in heparin-DOCA conjugates. In heparin-lauric acid and heparin-palmitic acid conjugates, similar amounts of alkanoic acid were coupled to heparin.

Example 4

Solubility Test of Heparin-DOCA Conjugate. Heparin can be dissolved in relatively few

20   solvents, such as water and formamide. The heparin derivatives of the present invention have a slightly hydrophobic property, thus it was anticipated that such derivatives would be soluble in

12

additional solvents. This was tested in the present example by assessing solubility in mixtures of

acetone and water as the solvent. In the case of heparin-DOCA conjugates, as the wt.% of

DOCA increased, the solubility of the conjugate in the solvent was increased. In the case of 14

wt% of DOCA, the heparin-DOCA conjugate was dissolved in 50:50 acetone-water, but the

5 conjugate was not dissolved in 70:30 acetone-water. In the case of 24 wt% of DOCA, the

solubility of the heparin-DOCA conjugate in the solvent was increased as the acetone content of

the solvent was increased. The solubility of heparin-DOCA (24%) in the solvent was maximized

at 50:50 volume ratio of acetone and water.

Example 5

10 Analysis on Separation of Heparin on Phenyl-Sepharose CL-4B Gel at 4°C. Phenyl-

Sepharose® CL-4B was used for removing the unreacted heparin from heparin-DOCA, heparin-

cholesterol, and heparin-alkanoic acid. In addition, it was useful for estimating the degree of

hydrophobicity in coupled heparin derivatives. A commercial heparin sodium preparation from

beef lung (anticoagulant activity, 140 USP units per mg) was obtained from Pharmacia Hepar

15 Co. (Franklin, Ohio). A Phenyl Sepharose CL-4B gel column was obtained from Pharmacia

Biotech (Sweden). The column (HR 16/30 I.D.) was washed with ten volumes of water and then

was equilibrated before use by washing with at least 40 ml of 50 mM phosphate buffer pH 7.0 for

20 minutes followed by 40 ml of 50 mM phosphate buffer pH 7.0 containing 1.7 M ammonium

sulfate and then 40 ml of 50 mM phosphate buffer pH 7.0. The solution of heparin (5 mg) and

20 hydrophobic heparin (5 mg) in the same phosphate buffer (5 ml) was loaded on the column, and

eluted with the gradient solvent respectively. The flow rate was 1 ml/min, and each 2-ml fraction

13

14

was collected by fraction collector. After elution on the column, the column was washed with

100 ml of water and 1.7 M ammonium sulfate to remove all of the heparin or heparin-DOCA

conjugates retained, and the collected fractions were mixed with Azure A (0.01 mg/ml) for 1

minute. Each fraction that included heparin or hydrophobic heparin was quantified by

5   monitoring the absorbance at 500 nm spectrophotometrically in a Varian CARY 1E UV/VIS

spectrometer.

The change in elution curves of heparin-DOCA conjugates in FPLC for the different

coupling ratios between heparin and DOCA was observed. Heparin was eluted with PBS as

eluent, but not with ammonium sulfate since heparin is very hydrophilic. Heparin-DOCA

10   conjugate was not eluted in PBS but was eluted in ammonium sulfate solution. As the

concentration of ammonium sulfate in the eluent increased, the hydrophobicity of the eluted

heparin conjugates also increased. The heparin-DOCA conjugate was completely eluted in 1.3

M ammonium sulfate solution, even if the content of DOCA was increased.

Example 6

15   Bioactivity of Heparin Derivatives. Anticoagulant activities of modified heparin

derivatives were determined by activated partial thromboplastin time (APTT) and Factor Xa

chromogenic assay, respectively. The antithrombogenic activities of the heparin derivatives were

measured by FXa chromogenic assay and APTT, respectively (FIG. 1). The bioactivity of

heparin used in these experiments had a potency of 140 units per mg. The bioactivities of all of

20   the heparin derivatives prepared in this study was above 70% compared to the bioactivity of

unmodified heparin. There was no difference in the bioactivities of the conjugates with respect

14

15

to the hydrophobic agents used for making the conjugates. The bioactivities of heparin

derivatives decreased slightly, however, with increasing amounts of hydrophobic agent in the

conjugates. When a conjugate containing 7 wt% of DOCA was tested, the relative bioactivity of

the heparin-DOCA conjugate was 93% according to the APTT assay and 80% by the FXa assay.

5   In contrast, when a conjugate containing 24 wt% DOCA was tested, the relative bioactivity of

such heparin-DOCA conjugate decreased to 71.5% (APTT) and 70.1% (FXa assay).

Example 7

Heparin Oral Delivery. Six rats, housed in the animal care facility at the Korea Animal

Center were fasted for 12 hours before dosing. Groups of rats weighing 250-300 g were

10   administered a single oral dose of heparin, high molecular weight heparin-DOCA, or low

molecular weight heparin-DOCA. Blood samples (0.5 ml) were collected serially by heparin

coated capillary mixed with 3.8% sodium citrate. Samples were collected prior to administration

of heparin or heparin derivatives and for 10 hours thereafter at hourly intervals. Plasma was

harvested by centrifugation and was frozen at below -20°C. Plasma heparin activity in each

15   sample was determined by APTT assays. The APTT bioassay was performed according to the

procedure of Example 6. Plasma APTT units were determined from clotting time, which was

measured by fibrometer.

In the case of low molecular weight heparin-DOCA (FIG. 2), the maximum clotting time

occurred at 4 hours after orally administering. The clotting time was back to the baseline after 10

20   hours. For the high molecular weight heparin-DOCA (FIG. 3), the maximum clotting time

occurred at 8 hours after oral administering. The clotting time was maintained above 20 minutes

15

16

after 10 hours. The high molecular weight heparin-DOCA had higher anticoagulant activity than

low molecular weight heparin-DOCA.

Example 8

Release Rate of Heparin Derivatives *In Vitro*. *In vitro* studies were performed by first

5   casting derivatized heparin in a PEO/PCL multiblock copolymer over polyethylene discs (2.22

cm diameter). PEO/PCL is a multiblock copolymer composed of alternating blocks of

poly(ethylene oxide) (MW about 2,000) and poly(ε-caprolactone) (MW about 2,000), wherein

the total molecular weight of the copolymer is about 30,000. The heparin derivative was mixed

with the polymer, dissolved in acetone/water, cast on the polyethylene discs, and then the solvent

10   evaporated. The lower sides of the discs were then attached to the bottom of a 50-ml vial. Each

disc was immersed in 20 ml of PBS buffer (pH 7.4, I = 0.15) and placed at a randomly allocated

position in a shaking water bath (Han Baek Scientific Co., Korea) at 37°C and 80 rpm. At

selected times, determined so that the heparin derivatives concentration in the release medium

would not exceed 10% of its saturated solubility at 37°C, samples were removed and assayed for

15   drug content by UV spectroscopy (530 nm) after mixing with azure A. At each sampling time

the entire release medium was removed and replaced with fresh pre-warmed PBS buffer.

Following the release study, the initial amount of heparin derivative in the PEO/PCL multiblock

copolymer film was calculated by summation of the cumulative amount released over 40 days,

and the amount remaining in the disc at 40 days. This was compared with the initial amount

20   calculated from the drug loading. The cumulative amount of heparin derivative released was

plotted against time and the percentages released were used in statistical comparisons performed

16

by repeated measures analysis of variance.

The heparin derivatives were released from the polymeric matrix with almost controlled release rate with a small burst effect. The burst effect was shown within 1 hour, and the released amount at the burst was about 10% of the loaded amount of drug (FIG. 4).

18